



70026 Modugno (Bari) Italy - Via Agrigento, 37/39 Z.I.
 Tel. (+39) 080 5358845 - Fax (+39) 080 5358822
 www.marmoplast.it - info@marmoplast.it

Technical Sheet **Idro Sinplastex**

**ITEM CODE
310**

Base filler paint

GENERAL INSTRUCTIONS

Description	<i>Base filler paint, matt, water based, for walls and wood. Sandable, good base for water-borne paints and water-borne topcoats. Very good finishing and covering. Excellent adhesion.</i>
Use	<i>Idro Sinplastex is ideal as a base for wood, masonite, plywood, plaster. It allows a very good anchoring for water-borne paints and a very good finishing.</i>
Packaging	<i>L 2,5 - L 0,75</i>
Colours	<i>White liquid.</i>

DIRECTIONS FOR USE

How to apply	<i>Substrate must be clean, dry and solid. Traces of grease must be eliminated. Mix carefully the product before using it and dilute it with water. Apply 2 coats with a 2 hours gap in between. It is possible to paint over it with water-borne paints.</i>
Pot life of mix	<i>N.A.</i>
Application temperature	<i>Between 10°C and 35°C. Humidity lower than 75%.</i>
Dilution	<i>Water.</i>
Recommended tools	<i>Roller, brush, airless machine.</i>
Tools cleaning	<i>With water, soon after use.</i>
Film final look	<i>Matt.</i>
Drying process at 20°	<i>Dust dry in about 1 hour, a deep one in 2 hours.</i>
Storage	<i>Keep the tank tightly closed, away from sources of heat, for a max of 12 months from production date shown on the tin.</i>
Cautions	<i>Use rubber gloves. Always use goggles and a mask when spraying. Aerate the room.</i>

This technical sheet is just informative. Colorificio Marmoplast has no responsibility with regards to a wrong application of the products.



70026 Modugno (Bari) Italy - Via Agrigento, 37/39 Z.I.
 Tel. (+39) 080 5358845 - Fax (+39) 080 5358822
 www.marmoplast.it - info@marmoplast.it

Technical Sheet **Idro Sinplastex**

ITEM CODE
310

Base filler paint

TECHNICAL DATA

Coverage rate	10mq/L per coat.
Hazard class	None.
Specific weight	1,55 Kg/L
pH	8,5
Viscosity	Brookfield a 20° C Vel. 20 Gir 6 = 18000 mPas ± 10%
VOC	13 g/l
PVC	n.a.
% SVR	60%
Certification	n.a.
Washability	n.a.
Brightness	n.a.
Adherence	n.a.
Notes	n.a.

This technical sheet is just informative. Colorificio Marmoplast has no responsibility with regards to a wrong application of the products.